

PULICOL 2000

Solvent gel for removing adhesives and paints



WHERE TO USE

For removing old natural and synthetic resin-based adhesives, paint and grouts/grout residue.

Some application examples

- Removing old adhesive from floors e. g. marble, ceramic tile, wood, concrete, cementitious levelling coats, metal, etc.
- Removing old adhesive from ceramic tiles and mosaic, marble, concrete, wood, gypsum, metal, fibrous concrete, etc.
- Removing paint from the surface of metal, wood, concrete, etc.

TECHNICAL CHARACTERISTICS

Pulicol 2000 is made from a mixture of unchlorinated solvents in gel form. It is easy to apply with a spatula or by brush and gives off very little odour.

Pulicol 2000 has high detachment capacity on films of resin-based adhesives and varnishes within just a few minutes of application.

RECOMMENDATIONS

- Do not mix **Pulicol 2000** with water.
- Do not use on substrates that can be damaged by solvents, e.g. certain plastics (rubber, PVC), surfaces treated with decorative enamel that are not resistant to solvents, or on varnished wood floors.
- Do not use **Pulicol 2000** on baking paint because it would have little effect.

APPLICATION PROCEDURE

Spread **Pulicol 2000** with a trowel or brush on the residues of adhesive or varnish which need to be removed. Wait 2-3 minutes, depending on the type of adhesive or varnish, and remove the **Pulicol 2000** together with the adhesive or varnish with a smooth trowel or high-pressure hydro-cleaning unit.

If the surface is smooth with low absorbency e.g. marble or ceramic, rinse off with plenty of water.

If the surface is rough and/or absorbent, e.g. cementitious screeds or scratch coats, remove the residue with sandpaper or a wire brush. Do not wash wood surfaces, sandpaper them only.

The amount of time **Pulicol 2000** should be left on before removing it depends on the type of adhesive and its thickness, for example:

- acrylic adhesives: requires a few minutes;
- polyurethane and epoxy-pol. adhesives: requires approx. 30 minutes;
- it may be necessary for a secondary application in certain circumstances.

COVERAGE

Coverage depends on the amount and type of adhesive: as a general rule, coverage is 0.3 kg/m².

PACKAGING

2.5 and 0.7 kg drums.

STORAGE

24 months in original sealed packaging.

The product complies with the conditions of Annex XVII to Regulation (EC) N° 1907/2006 (REACH), item 59.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Pulicol 2000 is highly flammable. We recommend, therefore, keeping the product away from naked flames, sparks and sources of heat (store in a cool place). Wear protective goggles and gloves when handling and applying the product. For further and complete information about the safe use of our product please refer to the latest version of our Material Safety Data Sheet.

PRODUCT FOR PROFESSIONAL USE.

TECHNICAL DATA (typical values)	
PRODUCT IDENTITY	
Consistency:	gel
Colour:	milky white
Density:	0.98
Storage:	24 months in original packaging
Flammable:	yes
APPLICATION DATA	
Waiting time before removal:	from 2 to 3 minutes depending on type of adhesive or varnish
Application temperature:	from +8°C to +35°C
Coverage (kg/m ²):	0.3

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website www.mapei.com.



ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.

569-12-2021 en (IT)

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

